

Magstripe for Bank Books

B10.6-2004-46

Measurements provided by Shannon Crawford-Taylor scrawford@cfcintl.com

24-Aug-04

Table 1 - Magtape hot stamped onto bank books

<u>Book #</u>	<u>Cover w/o mag. inch</u>	<u>Cover w/ mag. inch</u>	<u>Difference, inches</u>
1	0.0109	0.0108	-0.0001
2	0.0118	0.0115	-0.0003
3	0.0081	0.0077	-0.0004
4	0.0118	0.0110	-0.0008
5	0.0098	0.0097	-0.0001

Note: Thickness measured on magstripe and on cover immediately next to tape

Table 2 - psa magtape labels applied to bank books by hand

<u>Label #</u>	<u>Cover w/o mag. inch</u>	<u>Cover w/ mag. inch</u>	<u>Difference, inches</u>
1	0.0085	0.0124	0.0039
2	0.0078	0.0116	0.0038
3	0.0079	0.0111	0.0032

Note: Thickness measured on magstripe and on cover immediately next to label.

Table 3 - Thickness of psa magtape labels prior to application to bank books

<u>Label #</u>	<u>Label on liner, inch</u>	<u>Release liner, inch</u>	<u>Label calc'd, inch</u>
1	0.0079	0.0035	0.0044
2	0.0087	0.0053	0.0034
3	0.0067	0.0030	0.0037